



TECHNICAL INFORMATION SHEET

Style: 7763 (E406A)

October 17, 2019
 Polartec® 200

Certifications:
 CAFTA: Y Oeko-Tex: Y

PRODUCT INFORMATION

General Description: INSULATION Polartec® 200 Double Velour w/DWR Solid Recycled

Weight: 7.4 Oz. Square Yard % Tolerance: 07.5- To 07.5+
 251 Gm. Square Meter % Tolerance: 07.5- To 07.5+

Width: 60 in. Tolerance: Plus 2 in.
 152.4 cm. Tolerance: Plus 5 cm.
 Minimum cuttable width inside pins.

Fiber Content: 100% POLYESTER
 (Tolerance per Fiber +/-3 percentage points)

Recycled Percentage: 85%

Surface Face: Velour

Characteristics: Back: Velour

Avg. Piece Length: 52 Yards 47 meters

Minimum Piece Length: 15 Yards

Care: Machine Wash Warm (40C/105F) Normal cycle. Tumble Dry Low. Do Not Bleach. Do Not Dry Clean. Do Not Iron. Do Not Use Fabric Softeners.

Note: Instructions are for fabric care; actual garment care may vary depending on construction.

DESCRIPTIVE DATA *The following data is provided for descriptive purposes only and does not constitute specifications or standards unless indicated as such below or otherwise agreed to in writing.*

Test	Test Method	Specification Requirement
CPSC Flammability Fabrics Act	16CFR 1610.37d Exemption	Class 1
COLORFASTNESS TO CROCKING, DRY	AATCC 8	Min: 4.00 Max: 5.00
COLORFASTNESS TO CROCKING, WET		Min: 3.00 Max: 5.00
COLORFASTNESS TO LAUNDERING-STAIN, POLYESTER	AATCC 61, OPTION 2A (120F,50 STEEL BALLS,45 MIN	Min: 3.00 Max: 5.00
COLORFASTNESS TO LIGHT, 20 HOUR	AATCC 16, OPTION 3	Min: 4.00 Max: 5.00
SHRINKAGE, LENGTH	AATCC 135, 3X WASH 120F/3X TUMBLE DRY MEDIUM	Min: -5.00 % Max: 5.00 %
SHRINKAGE, WIDTH	AATCC 135	Min: -5.00 % Max: 5.00 %
STRETCH-LOOSE FIT, WIDTH	ASTM D2594, 5LB LOAD	Min: 50.00 % Max: 120.00 %



TECHNICAL INFORMATION SHEET

October 17, 2019

Polartec® 200

Style: 7763 (E406A)

Test	Test Method	Specification Requirement
WATER REPELLENCY: SPRAY, SAMPLE 1	AATCC 22, AS IS	Min: 80.00 Max: 100.00
WATER REPELLENCY: SPRAY, SAMPLE 2	AATCC 22	Min: 80.00 Max: 100.00
WATER REPELLENCY: SPRAY, SAMPLE 3		Min: 80.00 Max: 100.00
WEIGHT PER SQUARE YARD	ASTM D 3776, OPTION C	Min: 6.80 OZ/YD2 Max: 8.00 OZ/YD2